



Material & Engineering Laboratory-Taipei

## TEST REPORT

REPORT NO.: HV-17-05788A-1

PAGE: 1 OF 3

DATE: SEPTEMBER 14, 2017

AutoStrato Pte Ltd

No.52, Ln. 1129, Zhonghua Rd., Zhubei City, Hsinchu County 30267, Taiwan

The following merchandise was submitted and identified by the vendor as :

Product Name : Ceraz Ceramic Coating

Manufacturer/Supplier : AutoStrato Pte Ltd

We have tested the submitted sample(s) as requested and the following results were obtained :

Test Required : (According to client's test specification, please see following sheets in detail.)

Hardness by Pencil Test

Test Result :

-PLEASE SEE ATTACHED PAGE-

Date of Receive : SEPTEMBER 01, 2017

Date of Testing : SEPTEMBER 01, 2017 ~ SEPTEMBER 06, 2017

Signed for and on behalf of  
SGS Taiwan Ltd.

Carlos Kao  
Asst. Manager

The content of this PDF file is accordance with the original issued reports for reference only. This Test Report cannot be reproduced, except in full, without prior written permission of the Company. 此 PDF 電子檔內容係根據原簽發之紙本報告製作，僅供參考用。本報告未經本公司書面同意，不可部份複製。

## TEST REPORT

REPORT NO.: HV-17-05788A-1


PAGE: 2 OF 3

DATE: SEPTEMBER 14, 2017

### Hardness by Pencil Test

Test Equipment:

Name	Brand
Pencil	MITSU-BISHI uni



Lab Environmental Conditions:

Ambient Temperature: 23±2°C

Relative humidity: 50±5%RH

Test Method/ Specification:

JIS K5400(1990) Testing Methods for Paints (Scratch Hardness)

The variety of pencil hardness:

6B - 5B - 4B - 3B - 2B - B - HB - F - H - 2H - 3H - 4H - 5H - 6H - 7H - 8H - 9H  
 Soft ←-----→ Hard

Load: 1000 g

Test Result:

Above 9H


## TEST REPORT

REPORT NO.: HV-17-05788A-1

PAGE: 3 OF 3

DATE: SEPTEMBER 14, 2017

Test Photo:



— The End of Test Report —